

BE 15 EPOXY

MIXING RATIO BY WEIGHT

100:28

READY MIX, Kg	PART A, Kg	PART B, Kg
1	0,78	0,22
2	1,56	0,44
3	2,34	0,66
4	3,12	0,88
5	3,90	1,10
6	4,68	1,32
7	5,46	1,54
8	6,24	1,76
9	7,02	1,98
10	7,80	2,20
11	8,58	2,42
12	9,36	2,64
13	10,14	2,86
14	10,92	3,08
15	11,70	3,30
16	12,48	3,52
17	13,26	3,74
18	14,04	3,96
19	14,82	4,18
20	15,60	4,40